

Yunsheng Coatings Specification



Coating Type	Labeling	Color	Thickness	Anticorrosion Performance			Bonding Force	Working Temperature
				Salt Spray Test	Humidity Heat Test	Pressuer Cooker Test		
Epoxy	Electrophoresis	Black	>10μm	240h	240h	96h	15~50Mpa	< 130°C
	Spray	Black	>10μm	120h	120h	72h	15~30Mpa	< 160°C
NiCuNi	NiCuNi(barral)	Silver	>10μm	72h	500h	72h	3~15Mpa	< 200°C
	NiCuNi(rack)	Silver	>10μm	/	500h	72h	3~15Mpa	< 200°C
Zinc	White Zn	Silver	>5μm	24h	48h	/	5~15Mpa	< 70°C
	Color Zn	Color	>5μm	48h	72h	/	5~15Mpa	< 70°C
Metallic Paint	Everlube	Golden	>8μm	72h	240h	96h	10~30Mpa	< 180°C
	ZnAl	Silver	>10μm	500h	500h	96h	3~10Mpa	< 180°C

update: 2024.3.8